

Processing instructions

ebalta colour pastes can be used both for polyurethane- and epoxyresin systems.

In general the colour paste is mixed with the resin/component A, not more than 1-2 %, as the mechanical properties of the product might change.

Since it's a thixotropic paste, for low viscosity systems we recommend to make a colour batch previously. This way the production of a homogeneously coloured component is easier.

In General

For special applications, please feel free to contact our technicians.

sales package: 0,250 kg / 1,000 kg

Storing

Storage at room temperature 18-25 °C.

Opened containers should be closed immediately after use and should be used up as soon as possible.

Shelf life is indicated on the labels.

Safety measure

Please follow the precaution instructions of the Government Safety Organisation of the chemical industry when working with this material. Please follow safety advices !

Waste Disposal

According to arrangement with local authorities cured material can be disposed as domestic or commercial waste. Non-cured products are waste which is subject to inspection and has to be disposed accordingly. In case of further questions please do not hesitate to contact our Department for Product Safety.

The instructions and recommendations are given in good faith and are based on long experience and careful tests. Since the conditions of use are beyond our control, and due to versatility of applications and working methods, we can't give any guarantee. All information are non-binding and are no guarantee for special characteristics or properties of the product. Despite information given from **ebalta** the customer has to make his own tests regarding applications and processing. If any special warranty is requested, written agreement on this subject is essential.