

Basis	ebablock® 920
Colour	green

Applications

- Foundry patterns
- Core boxes
- Pattern plates
- fixtures
- Bath models for galvanic tools
- Construction- and maintenance gauges

Properties

- very easy to work
- good edge stability
- high quality surface
- dense surface
- high impact strength
- very low generation of dust during machining
- low coefficient of linear expansion

Processing data

Product	ebablock® 920	
Colour	green	
Density at 20°C	g / cm ³	1,22 ± 0,03

Physical data

Properties	Inspect. requirem.	Unit	Value
Flexural strength	EN ISO 178	MPa	110 ± 5
Flexural elongation at break	EN ISO 178	%	6,4 ± 0,2
Flexural modulus	EN ISO 178	MPa	3100 ± 200
Impact resistance (Charpy)	EN ISO 179	kJ/m ²	50 ± 10
Compressive strength	EN ISO 604	MPa	95 ± 5
Shore hardness	DIN ISO 7619-1	Shore D	85 ± 3
Heat resistance (HDT)	DIN EN ISO 75 B	°C	80 ± 3
coefficient of linear expansion 20 - 50 °C	internatl test / Dilatometer	10 ⁻⁶ K ⁻¹	ca. 87
Wear jet test	internal tests	W(V/t) [mm ³ /min]	ca. 91
Abrasion Taber Abraser H 18 Application weight 500g / 500 Rotations	internal	mg	ca. 72

Sales units (packages)

ebablock® 920

dimensions variable
(max. casting volume 160 ltr.)

ebaboard PW 920
1000 x 500 x 30 mm
1000 x 500 x 50 mm
1000 x 500 x 75 mm
1000 x 500 x 100 mm

Processing instructions

Advices for machining of block material

- Making even of milling support
- Roughing of geometry
- Remove clamps, if possible over night
- Clamping
- Finishing

Milling parameters available.

In General

ebablock® material is available as rough boards and blocks:

Advantages:

- Dense structure
- Jointless
- Low-stress
- Close to contour and variable measurements

Please take dimensional allowances into consideration regarding sizes of rough blocks and boards. We recommend an addition of 10 mm per dimension.

Dimension tolerances of 3 mm in length and width and 0,5 mm in thickness are possible.

During casting of a block/blank voids or colour shades may occur. Therefore we can not give any guarantee, that the block/blank is completely free from bubbles. In case of a casting thickness over 250 mm or complex contours we reserve the right to cast in parts. Colour shades, bubbles and parting lines are not considered as inferior quality.

Safety measure

ebablock® material is a cured filled polyaddition product, no hazardous dusts when grinding.

According to regulations for hazardous products all **ebablock®** products are not to be marked for transport and storage. Please follow safety advices !

Waste Disposal

Small quantities can be disposed as domestic waste. For big quantities please contact your local authorities. In case of further questions please do not hesitate to contact our department for product safety.

The instructions and recommendations are given in good faith and are based on long experience and careful tests. Since the conditions of use are beyond our control, and due to versatility of applications and working methods, we can't give any guarantee. All information are non-binding and are no guarantee for special characteristics or properties of the product. Despite information given from **ebalta** the customer has to make his own tests regarding applications and processing. If any special warranty is requested, written agreement on this subject is essential.