

Basis **soft casting resin**
 Resin **GM 951-1 Comp. A**
 Hardener **GM 951-1 Comp. B**

Colour black
 Further colours beige

Applications

- Casting mould for gypsum
- Casting mould for plastic
- Casting mould for wax
- Casting mould for ceramic materials
- Casting mould for PU-foam
- Casting mould for cement
- Gaskets
- Sealing profiles in core boxes
- fixtures

Properties

- shore A hardness 45
- well castable
- good tear propagation resistance
- RoHS conform

Processing data

Product		Mixture GM 951-1 / Comp. A+B	Resin GM 951-1 Comp. A	Hardener GM 951-1 Comp. B
Colour		black	black	transparent
Mixing ratio	p. b. w.		100	10
Viscosity at 25°C	mPas	4300 ± 200	6300 ± 1000	20 ± 10
Density at 20°C	g / cm ³	1,15 ± 0,03	1,18 ± 0,03	0,95 ± 0,03
Pot life 200 g / 20°C	min.	17 - 27	-	-
Curing time at RT	hrs.	7 - 10	-	-

Physical data

Properties	Inspect. requirem.	Unit	Value
Tensile strength / test piece type 2	ISO 37	MPa	2,0 ± 0,2
Elongation at break / test piece type 2	ISO 37	%	980 ± 100
Shore hardness	DIN ISO 7619-1	Shore A	45 ± 3
Tear resistance arch shaped test piece with incision 1 mm	DIN ISO 34-1	kN/m	5,5 ± 0,5

Sales units (packages)

Packing size	B-Pack	GM 951-1 / Comp. A+B	resin 10 x 0,800 kg + hardener 10 x 0,080 kg = 8,800 kg
Units	Comp. A	GM 951-1 Comp. A	15,000 kg
	Comp. B	GM 951-1 Comp. B	1,500 kg

Processing instructions

Material- and working- temperature: between 20 - 25 °C. Heat up moulds to min. 20°C before casting
Close containers after use.

Seal porous mould surfaces first (**ebalta** mould sealer).

For optimum mould releasing we recommend a special release agent (like T1-1), which can be applied easily with a brush or be sprayed. Releasing of the mould 2-3 times, evaporate for about 20 min. after each releasing.

In General

The product is a very soft elastic polyurea casting compound.

ebalta GM 951-1 is suitable as a flexible casting system in the field of mould- and tooling for parts which require low shore hardness and high tear propagation resistance due to deep under cuts.

Mould temperatures of about 60 °C lead and/or curing at 60°C, to faster curing and therefore short demoulding time. Demoulding can be reduced to 30-45 min.

To achieve final properties as fast as possible, postcuring can be made at 60°C for 6-8 hrs. and after curing at room temperature.

For complete curing of the parts, any non-postcured moulds should only be employed after 2-3 days. Any non-observance may lead to shorter pot life.

The potlife of GM 915-1 can be shortened by mixing hardener GM 951-1 with hardener GM 900-1 (see mixing table)

For individuell formulation of the shore hardness, GM 900-1 can be mixed with GM 951-1 (see mixing table).

With the A-component GM 951-1 Thix a spreadable surface resin can be obtained.

Storing

Storage at room temperature 18-25 °C.

Opened containers should be closed immediately after use and should be used up as soon as possible.

Shelf life is indicated on the labels.

Safety measure

Please follow the precaution instructions of the Government Safety Organisation of the chemical industry when working with this material. Please follow safety advices!

Waste Disposal

According to arrangement with local authorities cured material can be disposed as domestic or commercial waste.

Non-cured products are waste which is subject to inspection and has to be disposed accordingly.

In case of further questions please do not hesitate to contact our Department for Product Safety.

The instructions and recommendations are given in good faith and are based on long experience and careful tests. Since the conditions of use are beyond our control, and due to versatility of applications and working methods, we can't give any guarantee. All information are non-binding and are no guarantee for special characteristics or properties of the product. Despite information given from **ebalta** the customer has to make his own tests regarding applications and processing. If any special warranty is requested, written agreement on this subject is essential.