

Basis
Resin **PS 02**
Hardener

Colour grey

Applications

- Foundry patterns
- Core boxes
- Negatives
- Mould constructions

Properties

- glassfibre filled

Processing data

Product		Mixture	Resin PS 02	Hardener
Colour		grey	grey	blue
Mixing ratio	p. b. w.		100	12
Viscosity at 25°C	mPas	pastös	pasty	90 ± 15
Density at 20°C	g / cm ³	1,05 ± 0,02	1,06 ± 0,02	0,98 ± 0,02
Pot life 200 g / 20°C	min.	30 - 40	-	-
Curing time at RT	hrs.	12 - 16	-	-

Physical data

Properties	Inspect. requirem.	Unit	Value
Flexural strength	EN ISO 178	MPa	33 ± 3
Flexural elongation at break	EN ISO 178	%	0,85 ± 0,1
Flexural modulus	EN ISO 178	MPa	4600 ± 450
Impact resistance (Charpy)	EN ISO 179	kJ/m ²	4 ± 0,5
Compressive strength	EN ISO 604	MPa	60 ± 5
Heat resistance (Martens)	DIN 53458	°C	40 ± 2
Shore hardness	DIN ISO 7619-1	Shore D	80 ± 2
Coefficient of thermal expansion	internal test / Dilatometer	10 ⁻⁶ K ⁻¹	-

Sales units (packages)

Units Resin PS 02 20,000 kg / 25,000 kg refill box

Storing

At appropriate storage 18-25°C.

Occuring crystallization due to disadvantageous storage conditions can be made return by warming up the material at approx. 60° C.

Opened containers should be closed immediately after use and be protected against moisture. This material should be used up as soon as possible.

Shelf life: see labels

Safety measure

Please follow the precaution instructions of the Government Safety Organisation of the chemical industry when working with this material. Please follow safety advices !

Waste Disposal

According to arrangement with local authorities cured material can be disposed as domestic or commercial waste.

Non-cured products are waste which is subject to inspection and has to be disposed accordingly.

In case of further questions please do not hesitate to contact our Department for Product Safety.

The instructions and recommendations are given in good faith and are based on long experience and careful tests. Since the conditions of use are beyond our control, and due to versatility of applications and working methods, we can't give any guarantee. All information are non-binding and are no guarantee for special characteristics or properties of the product. Despite information given from **ebalta** the customer has to make his own tests regarding applications and processing. If any special warranty is requested, written agreement on this subject is essential.