Repair Putty



Basis aluminium filled

Resin

Hardener Hardener for polyester

Colour silver grey

Applications

Properties

Moulding tools

aluminium filled

· Foundry patterns

• high heat resistance

• In the automotive field

Processing data

Product		Mixture Repair Putty	Resin	Hardener Hardener for polyester
Colour		silver grey	grey	white
Mixing ratio	p. b. w.		100	1
Viscosity at 25°C	mPas	Paste	pastös	thixotrop
Density at 20°C	g / cm ³	1,46 ± 0,03	1,44 ± 0,02	1,15 ± 0,03
Pot life 200 g / 20°C	min.	5 - 15	-	-
polishable at RT after	min.	20 - 30	-	-

Physical data

Properties	Inspect. requirem.	Unit	Value
Flexural strength	EN ISO 178	MPa	-
Flexural elongation at break	EN ISO 178	%	-
Flexural modulus	EN ISO 178	MPa	-
Flexural elongation at break	ISO 37	%	-
Impact resistance (Charpy)	EN ISO 179	kJ/m²	-
Compressive strength	EN ISO 604	MPa	-
Shore hardness	DIN ISO 7619-1	Shore D	-
Heat resistance (HDT)	DIN EN ISO 75 B	°C	-

Sales units (packages)

Repair Putty

1,400 kg resin incl. hardener

tooling resins . blocks . auxiliaries . silicones

Revision: 0

as of: 09.03.2006

Repair Putty



Processing instructions

The substrate should be carefully cleaned from any dirt, grease and former paint residues and down to. After 20-30 minutes curing time the paste can be grinded in dry or wet condition. Reaction substrate (wash-primer), synthetic resin or nitro-combination primer are not suitable as substrate for **ebalta** repair paste, as there would probably occur adhesion difficulties with these substrates.

In General

ebalta repair paste is an aluminium containing two-component- moulding compound for repairing of defective moulds and tools made of metal or synthetic resin, as well as defective castings made of aluminium or iron. Casting voids can be filled, cracks can be cemented. Another ermarkable property is the heat resistantce of **ebalta** repairing paste. Suitable substrates are such as steel plate, aluminium and iron casting.

Working temperature range: 100 °C

Storing

Storage at room temperature 18-25 °C.

Already opened containers should be closed immediately after use and should be used as soon as possible.

Shelf life: see labels .

Safety measure

Please follow the precaution instructions of the Government Safety Organisation of the chemical industry when working with this material. Please follow safety advices!

Waste Disposal

According to arrangement with local authorities cured material can be disposed as domestic or commercial waste. Non-cured products are waste which is subject to inspection and has to be disposed accordingly. In case of further questions please do not hesitate to contact our Department for Product Safety.

The instructions and recommendations are given in good faith and are based on long experience and careful tests. Since the conditions of use are beyond our control, and due to versatility of applications and working methods, we can't give any guarantee. All information are non-binding and are no guarantee for special characteristics or properties of the product. Despite information given from **ebalta** the customer has to make his own tests regarding applications and processing. If any special warranty is requested, written agreement on this subject is essential.

tooling resins . blocks . auxiliaries . silicones

as of: 09.03.2006 Revision: 0 Page: 2